


Rhenofol® CG



Product name:	Rhenofol® CG
Manufacturer/supplier:	FDT FlachdachTechnologie GmbH & Co. KG Eisenbahnstraße 6-8 68199 Mannheim Germany
Production plant:	Mannheim
Type of application:	For loose-laid application under ballast on terraces, gravel and green roofs. These sealing membranes can be used as a moisture barrier (type A) and as a ground water barrier (type T). For the installation, the application guidelines of the manufacturer have to be observed.
FPC certificate no.:	1343-CPD-K060660.3 1343-CPD-K060660.5
FPC issue of certification:	06
European standard:	EN 13956/EN 13967
Product description:	Synthetic PVC-P roofing membrane with glass fleece reinforcement and not compatible with bitumen.
Standard membrane dimensions:	20 m x 2.05 m x 1.2 mm 15 m x 2.05 m x 1.5/1.8/2.0 mm

Rhenofol® CG 1.2–2.0 mm

Properties	EN standard	Results
External fire performance	DIN CEN/TS 1187	no standard
Reaction to fire	DIN EN ISO 11925-2 DIN EN 13501-1	class E
Water vapour property μ	DIN EN 1931 (method B)	18,000
Tensile strength	DIN EN 12311-2 (method B)	≥ 10 N/mm ²
Elongation at break	DIN EN 12311-2 (method B)	$\geq 200\%$
Joint peel resistance	DIN EN 12316-2	≥ 600 N/50 mm
Joint shear resistance	DIN EN 12317-2	≥ 900 N/50 mm (fracture outside the joint area)
Resistance to impact rigid substrate flexible substrate	DIN EN 12691	1.2 mm thickness \geq 500 mm 1.5 mm thickness \geq 650 mm 1.8 mm thickness \geq 800 mm 2.0 mm thickness \geq 1,450 mm
Resistance to static load	DIN EN 12730 (method A/B)	≥ 20 kg
Hail resistance rigid substrate flexible substrate	DIN EN 13583	≥ 20 m/s ≥ 30 m/s
Tear resistance	DIN EN 12310-2	≥ 150 N
Resistance to root penetration	FLL DIN EN 13948	root- and rhizome-resistant
Dimensional stability	DIN EN 1107-2	$\leq 0.05\%$
Foldability at low temperature	DIN EN 495-5	≤ -30 °C
Chemical resistance	DIN EN 1847 (List annexe C)	passed
UV exposure	DIN EN 1297	class 0 (5,000 h)
Watertightness	DIN EN 1928 (method B)	≥ 400 kPa

FDT legal notice

We refer emphatically to the fact, that all details mentioned, especially the application and utilisation recommendation for the products and their system accessories, have been developed under normal conditions, and based on our knowledge and experience. Appropriate storage and usage of the products are assumed. A warranty or reliability of a finished project cannot be deduced because of varying materials, substrates and differing work conditions, neither by any indications nor from verbal statements, irrespective of any legal positions. For the possible accusation that FDT acted intentionally or grossly negligent, the user has to supply evidence that they provided FDT with all information and details necessary for an appropriate and correct evaluation through FDT in written form, immediately available and complete. The user is responsible for ensuring that the products are suitable for the given application. It is FDT's right to change product specifications without notice. Property rights of third parties are to be considered. In addition our particular sales and delivery terms are valid. The latest version of our product data sheet is obligatory, which can be requested directly through FDT.

All information as well as all technical and drawing data comply with current technical standards and are based on our experience. National standards and regulations must be observed.

Technical changes reserved. As of May 2014. © 2014 FDT FlachdachTechnologie GmbH & Co. KG, Mannheim, Germany

Product information

Rhenofol CG – roofing membrane for loose-laid application under ballast, e.g. gravel or paving slabs on terraces, concrete on parking decks or with a green roof system

Rhenofol CG is a product made of non-rigid polyvinyl chloride (PVC-P), a roofing membrane with glass reinforcement according to DIN EN 13956 and not compatible with bitumen.

Due to the outstanding material characteristics, Rhenofol CG roofing membranes are ideal for single-ply application. Seam overlaps can be easily sealed with solvent or hot-air welding.

Characteristics

- Roofing membrane according to DIN EN 13956
- Non-shrinking according to DIN EN 1107-2 testing
- Weather-resistant
- Resistant to UV radiation
- Root- and rhizome-resistant according to the FLL method, tested on 1.5 mm and 1.2 mm thick membranes
- Reaction to fire: class E according to DIN EN 13501-1
- Resistant to standard exhaust gas from industrial and heating plants
- Outstanding resistance to natural ageing
- Thermal conductivity according to DIN 52612: 0.16 W/(m*K)
- Certified with an Environmental Product Declaration (EPD) according to ISO 14025 and EN 15804

Not resistant to:


Bitumen and tar-containing materials; organic solvents such as benzene, toluene, hydrogen chlorides; fats, oils, such as oily cements and forming oils. Not compatible with rigid polystyrene foam.

Quality assurance

Rhenofol CG is subject to constant in-house and external quality control. The in-house quality assurance system for the whole company has been certified according to DIN EN ISO 9001, the world's most strict quality standard, and is constantly monitored by TÜV SÜD Management Service GmbH.

Range of application:

Rhenofol CG is used for waterproofing in loose-laid applications under ballast with gravel or paving slabs, e.g. on terraces or parking decks or under green roof systems.



SIG Design & Technology
Mannheim House
Gelders Hall Road
Shepshed
Leicestershire LE12 9NH

www.singleply.co.uk
Tel: 01509 505714
Fax: 01509 505475