

Product Data Sheet April 2016

Armourplan PVC Cleaner

PVC Membrane Cleaner

Product Details

Material	Solvent Cleaner
Tin Size	5 Litre
Colour	Clear
Product Number	05501475





Introduction

Armourplan PVC Cleaner is a solvent based solution. To ensure a satisfactory hot air weld is achieved between Armourplan membranes contaminated by moisture and building site dust and dirt it may be necessary to use Armourplan PVC cleaner. It can also be used as a general cleaner to remove dirt or wet adhesive.

Features & Benefits

- Effective membrane weld preparation
- Cost effective solution

Tel: 01257 488 000

Sales: polymeric.sales.uk@iko.com

Technical: polymeric.technical.uk@iko.com

Armourplan PVC Cleaner Use

- 1. Wash / scrub the area of membrane where Armourplan PVC Cleaner is to be applied with warm soapy water.
- 2. Allow to dry.
- 3. Apply Armourplan PVC Cleaner to membrane using a clean lint free cloth wearing appropriate PPE in accordance with the MSDS.
- 4. Allow Armourplan PVC Cleaner to fully evaporate prior to welding.
- 5. If the membrane becomes wet or soiled after the preparation the cleaning regime is to be repeated

Storage

Store in a sealed container in dry conditions at a temperature between 5°C and 25°C. Shelf life 12 months in an unopened container, stored at the above temperature.

Typical Properties

Characteristic Properties	Armourplan PVC Cleaner
Base	Solvent
Solid Content	0 %
Viscosity	N/A
Colour	Clear
Tack Life	N/A
Coverage Rate	20 m²/litre
Flash Point	70 Deg C (PMCC)
Shelf Life	12 Months

Further Product Information

Full product literature, health & safety and technical sheets are available as downloads from our website: www.ikopolymeric.com or on request by email: polymeric.marketing@iko.com

Whilst every care is taken to see that the information given in this literature is correct and up to date it is not intended to form part of any contract or give rise to any collateral liability, which is hereby specifically excluded. Intending purchasers of our materials should therefore verify with the company whether any changes in our specification or application details or otherwise have taken place since this literature was issued.





Technical: polymeric.technical.uk@iko.com

