

# **Product Data Sheet**

**July 2016** 

# **Armourplan PVC Lap Cleaner**

## **PVC Membrane Cleaner**

## **Product Details**

Material	Solvent Cleaner
Tin Size	5 Litre
Colour	Clear
<b>Product Number</b>	05501485





# Introduction

Armourplan PVC Lap Cleaner is a solvent based solution. To ensure a satisfactory hot air weld is achieved between Armourplan membranes contaminated by moisture and building site dust and dirt it may be necessary to use Armourplan PVC cleaner. It can also be used as a general cleaner to remove dirt or wet adhesive.

#### **Features & Benefits**

- Effective membrane weld preparation
- Cost effective solution

Tel: 01257 488000

Sales: polymeric.sales.uk@iko.com

Technical: polymeric.technical.uk @iko.com

# **Armourplan PVC Cleaner Use**

- 1. Wash / scrub the area of membrane where Armourplan PVC Lap Cleaner is to be applied with warm soapy water.
- 2. Allow to dry.
- 3. Apply Armourplan PVC Lap Cleaner to membrane using a clean lint free cloth wearing appropriate PPE in accordance with the MSDS.
- 4. Allow Armourplan PVC Lap Cleaner to fully evaporate prior to welding.
- 5. If the membrane becomes wet or soiled after the preparation the cleaning regime is to be repeated

## **Storage**

Store in a sealed container in dry conditions at a temperature between 5°C and 25°C. Shelf life is 12 months in an unopened container, stored at the above temperature.


# **Typical Properties**

Characteristic Properties	Armourplan PVC Lap Cleaner
Base	Hydrocarbon Solvent
Solid Content	N/A
Viscosity	Non - Viscous
Colour	Colourless
Drying Time @20c	Approx. 5 minutes
Coverage Rate	20 m²/litre
Flash Point	-35 Deg C (PMCC)
Shelf Life	12 Months

# **Further Product Information**

Full product literature and technical sheets are available as downloads from our website: www.ikopolymeric.com or on request by email: polymeric.marketing@iko.com

Whilst every care is taken to see that the information given in this literature is correct and up to date it is not intended to form part of any contract or give rise to any collateral liability, which is hereby specifically excluded. Intending purchasers of our materials should therefore verify with the company whether any changes in our specification or application details or otherwise have taken place since this literature was issued.





Technical: polymeric.technical.uk @iko.com

Sales: polymeric.sales.uk@iko.com

Tel: 01257 488000

